Toner
Water
(eco) Solvent
UV Curable
Latex

IJM022(C) Standard Plus Paper - FSC® 90 g/m²

Product Description
IJM022 Standard Plus Paper is an FSC-certified, surface-treated plotter paper. Both paper sides have had the same surface treatment. Prints on Standard Plus perform well in relative humid circumstances (splash-water proof). The pigment and dye-based ink adhesion is good. Standard Plus is a high-performance paper for transactional printing.

Physical Properties

Thickness (μm)	108 ± 4	ISO 534		Whiteness CIE	164 ± 3	Elrepho 3000 D65 10XLAV
Weight (g/m²)	90 ± 3	ISO 536		Opacity (%)	>96	Elrepho 3000 D65 10XLAV
Stiffness* (mN)	170 ± 15 / 68 ± 10	ISO 2493 (15°; 10 mm)		Roughness** (ml/min)	125 ± 25	ISO 8791

*MD/CD   **FS/BS

Applications/ features
Colour and monochrome CAD and GIS plots
High white
Splash-water proof
Both side surface treated
ECF pulp wood-free
ISO 9706 / DIN 6738 standard for permanence
ISO 9001 / 14001 certified
FSC certified

Available Widths (mm)

| 2"core | 297 | 420 | 594 | 841 | 914 | 610 | 841 | 914 | | |
| 3"core | | 420 | 594 | 841 | 914 | | | | | |

Refer for our current offering to mediaguide.oce.com

Storage Conditions
Temperature 21°C, Relative Humidity 50%
Repack opened rolls when not in use.

Print Conditions
Best results are obtained between 20 ± 3ºC and 50 ± 5 % RH.

Environment, Health & Safety
No Material Safety Data Sheet required. Waste can be handled as paper waste.

Lamination Compatibility

Cold	Warm	Hot
yes	no	no

Cold: pressure sensitive
Warm: heat activated: 85°C - 95°C
Hot: heat activated: 105°C -130°C

Outdoor Use
This surface treated paper is designed for indoor use and splash-water proof.

Colour Profiles
Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
Check availability of profiles for your printer on mediaguide.oce.com

Canon

Processing Guidelines

It is recommended to handle the media with cotton gloves Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. Insert media with care in the printers. Incorrect loading can cause skewing or creasing. Allow material to adapt to room conditions for 24 hours before printing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printers.

Ink/toner restrictions and printer settings have to be set for specific printers to obtain the best results. Canon colour profiles include recommended ink restrictions and printer settings for Canon supported printers.

Canon